ELASTOFLEX® S6 SBS INTERPLY/BASE MEMBRANE - 2.5mm (180g)

PRODUCT DESCRIPTION

Elastoflex S6 is a smooth surface Styrene-Butadiene-Styrene (SBS) modified bitumen roofing membrane reinforced with a polyester mat saturated with a rubberized asphaltic compound. Elastoflex S6 is available with either a sand or film top surface and a sanded bottom surface.

Elastoflex S6 is designed for use as an interply or base sheet to be applied using hot asphalt or approved cold processes. When a top surface film configuration is selected, successive system layers can be heat welded or self-adhered to Elastoflex S6.

TYPICAL APPLICATIONS

- High-quality SBS modified membrane in multi-ply roofing assemblies
- New roofing, re-roofing or re-cover roof systems and flashing details
- Hot asphalt and cold process installation methods

FEATURES AND BENEFITS

- Exceptional long-term weathering performance
- Superior flexibility, puncture resistance and dimensional stability
- Ease of application over approved substrates

TECHNICAL DESCRIPTION

TEST METHOD	PROPERTY	ASTM VALUE
ASTM D228	Net mass/unit area, min,lbs/100 ft2 (g/m2)	45 (2197)
ASTM D5147	Bottom side coating thickness, min, mm, (mils)	40 (1.0)
ASTM D5147	Maximum load at 73.4 ± 3.6°F (23 ± 2°C), MD & XMD, min, before and after heat conditioning, lbf/in. (kN/m)	30 (5.3)
ASTM D5147	Elongation at 73.4 ± 3.6°F (23 ± 2°C), MD & XMD, min, at maximum load, before and after heat conditioning, %	2
ASTM D5147	Tear strength at 73.4 ± 3.6 °F (23 ± 2 °C), min, lbf	35
ASTM D5147	Low temperature flexibility, max, before and after heat conditioning, °F (C)	O (-18)







PRODUCT DATA

Coverage (Approx)	150 sq ft
Weight (Approx)	90 lbs
Thickness (Nominal)	2.5 mm; 100 mils
Roll Size 15m x 1m	n (49'3" x 39 ³ / ₈ ")
Rolls/Pallet	25

APPLICABLE STANDARDS

- ASTM D6164, Type I
- UL Classified for use in class A, B or C roofs, as listed the latest UL "Roofing Materials and Systems Directory"
- Factory Mutual Approved
- CAN/CGSB 37-GP-56M Type 2a, Class C









ELASTOFLEX® S6 SBS INTERPLY/BASE MEMBRANE - 2.5mm (180g)

APPLICATION INSTRUCTIONS

Elastoflex S6 is intended to be used as a base sheet or interply in new or re-roof applications. Elastoflex S6 may be adhered directly to non-combustible substrates. Elastoflex S6 requires the installation of a compatible surfacing or cap sheet to complete the roofing system.

- Apply over clean, dry, dust and debris-free substrates. Prime concrete decks prior to application with PG 100 Asphalt Primer.
- When re-roofing, remove all prior roofing materials down to a clean debris-free substrate and properly remove all abandoned roof penetrations.
- Concrete or steel decks shall be designed with proper expansion devices.
- Wood decks shall have all joints blocked and properly supported.
- Ensure the fire rating of the assembly over any substrate.
- Ensure the installation of Elastoflex S6 does not prevent the ventilation of existing construction.
- Do not apply directly over shingles or existing membrane roofing.
- While installing Elastoflex S6:
 - 1. Start at the low point of the roof.
 - 2. Unroll the material and allow to relax prior to installation.
 - 3. Install in a solid mopping of type III or type IV asphalt, PG 350 or Polyplus 35 Mod Bit adhesive.
 - 4. Position successive rolls providing a minimum 15cm (6") end lap and 7.6cm (3") side lap.
- Details and flashing may be installed using hot asphalt, cold application or torch techniques. Check project details for proper installation requirements

POLYGLASS U.S.A., INC. MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc. 1111 West Newport Center Drive Deerfield Beach, FL 33442 www.polyglass.us

General Line: (888) 410-1375

(954) 233-1330

Customer Service: (800) 222-9782 Technical Service: (866) 802-8017

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 2 years. Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control.

For most current product data and warranty information, visit www.polyglass.ca

