

EverGuard® Fleece-back TPO 45 mil Membrane

Applicable Standards

UL Listed, FM Approved, Miami-Dade County Approved, Florida Building Code Approved, CRRC Listed, Title 24 Compliant*, ENERGY STAR® Qualified**, ASTM D6878.

Physical Properties	ASTM Test Method	ASTM D6878 Minimum	EverGuard® Typical Test Data
1. Certain data is provided in MD (machine direction) x CMD (cross machine direction) format. 2. Data is based upon typical product performance, and is subject to normal manufacturing tolerance and variance.			
Nominal Thickness	ASTM D751	0.039" (min.) (0.99 mm)	0.045" (1.14 mm)
Breaking Strength	ASTM D751 Grab Method	220 lbf/in. (38.5 kn/m)	375 lbf x 330 lbf (559 x 492 kg/m)
Factory Seam Strength	ASTM D751	66 lbf (98.34 kg/m)	115 lbf (membrane failure) (171 kg/m)
Elongation at Break	ASTM D751	15%	30%
Heat Aging	ASTM D573	90% Retention of Breaking Strength and Elongation at Break	100%
Tear Strength	ASTM D751 8" x 8" (203 x 203 mm) Sample	55 lbf (81.95 kg/m)	90 lbf x 120 lbf (134 x 179 kg/m)
Puncture Resistance	FTM 101C Method 2031	Not Established	>350 lbs. (159 kg)
Cold Brittleness	ASTM D2137	-40°C	-40°C
Permeance	ASTM E96	Not Established	0.08 Perms
Dimensional Change	ASTM D1204 @158°F (70°C), 6 hrs.	+/-1%	0.2%
Water Absorption	ASTM D471 @158°F (70°C), 1 week	+/-3.0% max.	0.7%
Hydrostatic Resistance	ASTM D751 Method D	Not Established	390 psi
Ozone Resistance	ASTM D1149	No visible deterioration @ 7 x magnification	No visible deterioration @ 7 x magnification
Reflectivity (white) Initial/Aged	ASTM C1549	N/A	0.76/0.68
Emissivity (white) Initial/Aged	ASTM C1371	N/A	0.90/0.83
Weather Resistance	ASTM G155/D6878	10,080 KJ/(m² · nm) at 340 nm	>20,000 KJ/(m² · nm) at 340 nm
Heat Aging	ASTM D573	240°F (115°C) for 32 weeks	60 weeks
Thickness Above Scrim	ASTM D7635	Min 30% of Total Thickness	15.8 mil (Nominal)
Guarantee			
Up to 20 years			

*White Membrane Only

**ENERGY STAR® only valid in the USA

Product Data

Roll Size	Note: Product sizes, dimensions, and widths are nominal values and are subject to normal manufacturing/packaging tolerance and variation.				
	Colors	Full Size Roll	Full Roll Weight	Half Roll Size	Half Roll Weight
	White, Tan, Gray	10' x 100' (3.05 x 30.5 m) (1,000 sq. ft. [92.9 sq.m])	270 lbs. (122 kg)	5' x 100' (1.52 x 30.5 m) (500 sq. ft. [46.5 sq.m])	144 lbs. (65 kg)
Note: Membrane rolls shipped horizontally on pallets, stacked pyramid-style and banded.					
Storage	Store rolls on their sides on pallets or shelving in a dry area.				
Safety Warning	Membrane rolls are heavy. Position and install by at least two people.				



Quality You Can Trust...
From North America's
Largest Roofing Manufacturer!™

gaf.com