



WATERPROOFING

APPLICATIONS

ROOFS

ELASTOPHENE SANDED

TECHNICAL DATA SHEET 200316SCANE

(supersedes 030610CAN8E)

DESCRIPTION

ELASTOPHENE SANDED is a base sheet membrane composed of SBS modified bitumen and a glass mat reinforcement. Both sides are sanded.

INSTALLATION

HOT BITUMEN

ELASTOPHENE SANDED is unrolled in a bed of hot bitumen (SEBS or oxidized) applied with a mop.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

Specifications	ELASTOPHENE SANDED
Thickness	2.2 mm (87 mils)
Reinforcement	Glass mat
Dimensions	15 x 1 m (49 x 3.3 ft)
Weight	2.7 kg/m ² (0.6 lb/ft ²)
Selvedge width	75 mm (3 in)
Surface	Sanded
Underface	Sanded

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ELASTOPHENE_SANDED.indd



WATERPROOFING

APPLICATIONS

ROOFS

ELASTOPHENE SANDED

TECHNICAL DATA SHEET 200316SCANE

(supersedes 030610CAN8E)

PROPERTIES

As per CSA A123.23-15, Type A, Grade 3.

Properties	ELASTOPHENE SANDED	
	BEFORE Heat Conditioning	AFTER Heat Conditioning
Strain energy, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	0.5/0.45 kN/m (2.8/2.6 lbf/in) 0.4/0.4 kN/m (2.3/2.3 lbf/in)	0.4/0.3 kN/m (2.3/1.7 lbf/in) 0.4/0.3 kN/m (2.3/1.7 lbf/in)
Peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	13/8 kN/m (74/46 lbf/in) 21/21 kN/m (120/120 lbf/in)	18/12 kN/m (103/68 lbf/in) 21/18 kN/m (120/103 lbf/in)
Elongation at peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	4/3 % 4/4 %	4/4 % 3/3 %
Ultimate elongation, MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F)	21/27 %	5/5 %
Dimensional stability, max MD/XD	±0.2/±0.2 %	
Low temperature flexibility, max MD/XD	-18/-18 °C (0/0 °F)	-18/-18 °C (0/0 °F)
Compound stability at 91 °C (196 °F)	107/107 °C (225/225 °F)	

(All values are nominal)

STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ELASTOPHENE_SANDED.indd