



WATERPROOFING

APPLICATIONS

ROOFS

SOPRALENE 180 SANDED

TECHNICAL DATA SHEET 200316SCANE

(supersedes 121031SCAN1E)

DESCRIPTION

SOPRALENE 180 SANDED is a base sheet membrane composed of SBS modified bitumen and a non-woven polyester reinforcement. Both sides are sanded.

INSTALLATION

HOT BITUMEN

SOPRALENE 180 SANDED is unrolled in a bed of hot bitumen (SEBS or oxidized) applied with a mop.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

Specifications	SOPRALENE 180 SANDED
Thickness	3.0 mm (118 mils)
Reinforcement	Non-woven polyester
Dimensions	10 x 1 m (33 x 3.3 ft)
Weight	3.6 kg/m ² (0.7 lb/ft ²)
Selvedge width	75 mm (3 in)
Surface	Sanded
Underface	Sanded

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_SOPRALENE_180_SANDED.indd

1/2



WATERPROOFING

APPLICATIONS

ROOFS

SOPRALENE 180 SANDED

TECHNICAL DATA SHEET 200316SCANE

(supersedes 121031SCAN1E)

PROPERTIES

As per CSA A123.23-15, Type B, Grade 3.

Properties	SOPRALENE 180 SANDED	
	BEFORE Heat Conditioning	AFTER Heat Conditioning
Strain energy, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	6.5/6.5 kN/m (37/37 lbf/in) 8.0/4.0 kN/m (46/23 lbf/in)	5.5/5.5 kN/m (31/31 lbf/in) 3.1/3.1 kN/m (18/18 lbf/in)
Peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	15/11 kN/m (86/63 lbf/in) 22/17 kN/m (126/97 lbf/in)	14/10 kN/m (80/57 lbf/in) 19/11 kN/m (108/63 lbf/in)
Elongation at peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	50/60 % 30/30 %	15/50 % 7/21 %
Ultimate elongation, MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F)	55/70 %	45/45 %
Dimensional stability, max MD/XD	±0.5/±0.1 %	
Low temperature flexibility, max MD/XD	-18/-18 °C (0/0 °F)	-18/-18 °C (0/0 °F)
Compound stability at 102 °C (216 °F)	121/121 °C (250/250 °F)	
Resistance to puncture	Pass	

(All values are nominal)

STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_SOPRALENE_180_SANDED.indd

2/2