# **PARADIENE 20 EG**



Commercial Product Data Sheet

### **Product Description**

Paradiene 20 EG is a high performance, heavy duty, modified bitumen base ply designed for use in homogeneous multi-layer modified bitumen roof membrane systems. Paradiene 20 EG consists of a fiberglass scrim/fiberglass mat composite impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen.

#### **Product Uses**

Paradiene 20 EG is the first ply of all Siplast Paradiene 20 EG/30 Systems, and is lapped 3 inches (7.6 cm) at sides and 6 inches (15.2 cm) at ends. Paradiene 20 EG is specifically designed for use in conjunction with Paradiene systems requiring high tensile and high elongation performance. Paradiene 20 EG can be applied in approved Type IV asphalt or Siplast PA-311 Adhesive. Contact Siplast for specific approval on other product uses.

#### **Product Approvals**

Paradiene 20 EG is approved by Factory Mutual Research (FM Standard 4470) for use in Siplast Paradiene 20 EG/30, Paradiene 20 EG/30 FR, Paradiene 20 EG/20 PR, Paradiene 20 EG/Veral, and Paradiene 20 EG/Parafor Class 1 insulated steel roof deck constructions and insulated and non-insulated concrete roof deck constructions, subject to FM conditions and limitations.

Paradiene 20 EG is approved by Underwriters Laboratories for use in <sub>c</sub>UL<sub>us</sub> Classified Siplast Paradiene 20 EG/30, Paradiene 20 EG/30 FR, Paradiene 20 EG/20 PR, Paradiene 20 EG/Veral, and Paradiene 20 EG/Parafor Roof Systems. Siplast Paradiene 20 EG/30 FR and Paradiene 20 EG/Veral have been classified by Underwriters Laboratories as a Class A roofing system over non-combustible, insulated non-combustible, and insulated combustible decks. Siplast Paradiene 20 EG/30 FR has been classified by Underwriters Laboratories as a Class B roofing system over combustible decks. Siplast Paradiene 20 EG/20 PR has been classified by Underwriters Laboratories as a Class A roofing system over non-combustible and insulated non-combustible decks when surfaced with roofing gravel. Siplast Paradiene 20 EG/30 and Paradiene 20 EG/Parafor have been classified as a Class C roofing system over combustible, non-combustible, and insulated combustible decks.

Paradiene 20 EG meets or exceeds the requirements of ASTM D 6163 Type II, Grade S, and CGSB 37-GP-56M Type 2, Class C, Grade 2 for SBS-modified bituminous sheet materials using glass fiber reinforcements.

Siplast Roof Systems also have received the approval of many regional and local authorities. Please contact Siplast for specific information as required.

COMMERCIAL PE	RODUC Roll	ODUCT INFORMATION			
Coverage:	1.0 Square		(9.3 m²)		
Coverage Weight					
Per Square:	Min:	84 lb	(4.1 kg/m²)		
Roll Length:	Min:	33.5 ft	(10.21 m)		
Roll Width:	Avg:	3.28 ft	(1.00 m)		
Thickness:	Avg:	118 mils	(3.0 mm)		
	Min:	114 mils	(2.9 mm)		
Selvage Width:	N/A				
Selvage Surfacing:	N/A				
Top Surfacing: Silic	a parting	gagent			

Back Surfacing: Silica parting agent

Lines: Two laying lines are placed 3 in (7.6 cm) and 4 in (10.2 cm) from each edge of the material. The line color for this material is blue.

Packaging: Rolls are wound onto a compressed paper tube. The rolls are placed upright on pallets cushioned with corrugated cardboard and are adhered with adhesive at the labels. The top of the palleted rolls is covered with foilized Kraft paper. The palleted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet. Number Rolls Per Pallet: 25 Number Pallets Per Truckload: 18 Minimum Roll Weight: 84 lb (38.1 kg)

Storage and Handling: All Siplast roll roofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Canada Web site at www.Siplast.ca.



## **PARADIENE 20 EG**

Physical and Mechanical Properties

Property	CGSB	ASTM
(as Manufactured)	Test Method	Test Method
Roll Size	33.5 ft x 3.28 ft	33.5 ft x 3.28 ft
	(10.21 m x 1 m)	(10.21 m x 1 m)
Thickness (minimum)	N/A	114 mils (2.9 mm)
Thickness (average)	N/A	118 mils (3.0 mm)
Minimum Weight per Roll	N/A	84 lb (38.1 kg)
Low Temperature Flexibility	-22°F (-30°C)	-13°F (-25°C)
<sup>1</sup> Tensile Strength or Peak Load at 73ºF (23ºC) (average)	935 N/5 cm	80 lbf/inch (14.1 kN/m)
<sup>1</sup> Elongation at Peak Load at 73ºF (23ºC) (average)	5%	5%
<sup>1</sup> Ultimate Elongation at 73°F (23°C) (average)	100%	100%
Static Puncture	> 10 kg	N/A
Dimensional Stability (maximum)	0.1%	0.1%

Test methods and tolerances: CGSB 3

CGSB 37-GP-56M (1980), ASTM D 5147, and ASTM D 146 (weight)

1. The value reported is the lower of either MD or XD.