

Formerly known as SOPRAFLASH STICK 40

# SOPRAFLASH STICK DUO

TECHNICAL DATA SHEET 200316SCANE

(supersedes 150312SCAN8E)



WATERPROOFING

APPLICATIONS

ROOFS

## DESCRIPTION

SOPRAFLASH STICK DUO is a base sheet membrane composed of SBS modified bitumen and a glass mat reinforcement. The surface is sanded and the self-adhesive underface is covered with a silicone release film.

SOPRAFLASH STICK DUO is provided with **DUO SELVEDGE** technology which allows the immediate sealing of the membrane along side laps.

## SURFACE PREPARATION

Surfaces must be clean, dry and free of loose particles. The membrane is installed over the substrate previously primed with one of the **ELASTOCOL STICK** primers.

## INSTALLATION

### SELF-ADHESIVE

SOPRAFLASH STICK DUO is adhered to the substrate by peeling off the silicone release film.

Once the membrane is in place, apply pressure over the whole surface using a membrane roller to ensure a complete and uniform adhesion.

When completing the end lap, apply **ELASTOCOL STICK** primer over the last 150 mm (6 in) of the membrane before installing the next membrane.

Finish the application by welding the last 25 mm (1 in) of the side lap using an electric hot-air welder and a membrane roller. The use of **SOPRAMATIC** automatic hot-air welder will greatly increase the speed and quality of the seal.

Minimum application temperatures: 0 °C (32 °F).

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## PACKAGING

Specifications	SOPRAFLASH STICK DUO
Thickness	2.5 mm (98 mils)
Reinforcement	Glass mat
Dimensions	15 x 1 m (49 x 3.3 ft)
Weight	3.0 kg/m <sup>2</sup> (0.6 lb/ft <sup>2</sup> )
Selvedge width	100 mm (4 in)
Surface	Sanded
Underface	Self-adhesive, covered with a silicone release film

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS\_SOPRAFLASH\_STICK\_DUO.indd

Formerly known as SOPRAFLASH STICK 40

# SOPRAFLASH STICK DUO



WATERPROOFING

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 200316SCANE

(supersedes 150312SCAN8E)

## PROPERTIES

As per CSA A123.23-15, Type A, Grade 3.

Properties	SOPRAFLASH STICK DUO	
	BEFORE Heat Conditioning	AFTER Heat Conditioning
Strain energy, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	1/1 kN/m (5.7/5.7 lbf/in) 0.5/0.5 kN/m (2.8/2.8 lbf/in)	2.1/0.5 kN/m (12/2.8 lbf/in) 0.5/0.4 kN/m (2.8/2.3 lbf/in)
Peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	12/13.5 kN/m (69/77 lbf/in) 23/21 kN/m (131/120 lbf/in)	18/16 kN/m (103/91 lbf/in) 21/21 kN/m (120/120 lbf/in)
Elongation at peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	6/7 % 4/4 %	8/5 % 3/4 %
Ultimate elongation, MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F)	35/30 %	10/7 %
Dimensional stability, max MD/XD	±0.3/±0.1 %	
Low temperature flexibility, max MD/XD	-30/-30 °C (-22/-22 °F)	-18/-18 °C (0/0 °F)
Compound stability at 102 °C (216 °F)	107/107 °C (225/225 °F)	

(All values are nominal)

## STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS\_SOPRAFLASH\_STICK\_DUO.indd