

TECHNICAL DATA SHEET - RCABC

ISO 9001 - 2008 REGISTERED FACILITY

STOCK NO. 7704XXX

JULY, 2016

PREVENT TP HD CAP

This product is reinforced with a tough non-woven reinforced composite polyester mat, which has been strengthened with selected glass fiber strands. Specially formulated for excellent fire resistance, it is coated and impregnated with SBS modified bitumen to a thickness of 4.0 mm (158 mils). Ceramic, mineral granules are embedded in the surface to provide protection against ultraviolet radiation, and a light poly-film is bonded to the underside (which disappears upon heat-welding). Prevent TP HD can be used as a protective cap for a conventional BUR system, as the top ply in a two-ply Torchflex system, or as the top ply in a flashing installation. This product will easily satisfy the requirements of CGSB-37.56-M and ASTM D6162 Type I, Grade G. It also qualifies for a Class A rating in accordance with CAN/ULC S107M, UL790 and ASTM E108. Please contact your IKO Technical Representative for specific slope requirements. IKO's roofing products are produced and designed with consideration for environmental responsibility and sustainability, incorporating quality recycled components whenever possible, manufactured in facilities that comply with the most stringent government environmental regulations, and can therefore be a part of any "green" construction project.

CHARACTERISTIC		UNITS	NOMINAL VALUE	SPECIFICATION	TEST METHOD**	STANDARD LIMITS
ROLLS PER PALLET:		-	32	-	-	N/A
PALLET SIZE:		cm (in)	132 x 112 52 x 44	-	-	-
LENGTH:		m (ft)	8 (26.2)	-	-	± 1%
WIDTH:		mm (in)	1005 (39.6)	-	-	±6 (1/4)
WEIGHT:		kgs (lbs)	37.8 (83.3(-	-	-
THICKNESS:		mm (mils)	4.0 (158)	-	-	± 0.4 (16)
COLD FLEX:		°C (°F)	PASS	ASTM D6162	ASTM D5147	MIN: -18 (0)
STRAIN ENERGY @ 23°C	MD: XD:	kN/m	7.3 6.6	CGSB-37.56-M	CGSB-37.56-M	MIN: 5.5*
TENSILE STRENGTH	MD: XD:	kN/m	20.4 15.6	ASTM D6162	ASTM D5147	MIN: 13.1
ULTIMATE ELONGATION	MD: XD:	%	76.3 83.4	ASTM D6162	ASTM D5147	MIN: 26
TEAR STRENGTH	MD: XD:	N	71 69	CGSB-37.56-M	CGSB-37.56-M	MIN: 20*
LAP STRENGTH (5D @ 23°C)		kN/m	12	CGSB-37.56-M	CGSB-37.56-M	MIN: 4*
GRANULE LOSS:		g	0.26	ASTM D6162	ASTM D5147	MAX: 2.0
STATIC PUNCTURE:		N	PASS	CGSB-37.56-M	CGSB-37.56-M	<u>></u> 150*

^{*} CGSB-37.56-M revision, 9th draft, dated January 1997.

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.

^{**} Although both ASTM and CGSB may have requirements for a particular test, only the more stringent is indicated.