

ELASTOFLEX V 22

SBS (ELASTOMERIC) BASE/INTERPLY SHEET

PRODUCT DESCRIPTION

Elastoflex V 22 is a Styrene-Butadiene-Styrene (SBS) modified bitumen roofing membrane base sheet. This higher quality membrane is reinforced with a high quality fiberglass mat to ensure strength and excellent dimensional stability to the product. Elastoflex V 22 exhibits superior waterproofing and weathering physical properties.

The top and bottom surfaces are available in sand or factory applied burn-off film. Application methods include mechanically attached, hot asphalt, heat-welded, or as part of cold-applied system. When the top of membrane is surfaced with film, Elastoflex V 22 can be used as a base sheet in self-adhered systems.

Elastoflex V 22 membrane can be used as part of a Polyglass warranted multi-ply system, when combined with Elastoflex V G cap sheets or other approved Polyglass base sheets.

TYPICAL APPLICATIONS

- Use as a base or interply membrane in multi-ply low-slope roofing assemblies.
- Fastened anchor sheet, hot asphalt, cold adhesives or heat fused.
- New roofing, re-roofing and flashing reinforcement.

FEATURES AND BENEFITS

- Versatile for multiple application methods.
- High quality fiberglass mat enhances strength and dimensional stability.
- Provides a strong and durable substrate for other roofing membrane plies.

APPLICATION INSTRUCTIONS

Elastoflex V 22 is intended to be used as a base sheet or interply for new or re-roof applications. Elastoflex V 22 may be applied directly to non-combustible substrates. Elastoflex V 22 requires the installation of an interply and/or compatible granulated cap sheet to complete the roofing system.

- Apply over clean, dry, dust and debris-free substrates. When fully bonding, prime concrete decks and required substrates, prior to application with PG 100 Fast-Drying Asphalt Primer or applicable ASTM D-41 asphalt primer.
- When re-roofing, remove all prior roofing materials down to a clean, dust free substrate. Remove unused or abandoned through-roof penetrations.
- All substrates shall be designed with proper expansion devices.
- Wood decks shall have all joints cross blocked and/or properly supported.
- Installation of Elastoflex V 22 should not adversely affect the ventilation of existing construction.
- Do not apply directly to existing shingles or other unacceptable roof coverings.
- While installing Elastoflex V 22:
 1. Start at the lowest point of the roof.
 2. Unroll the material and allow it to relax as membrane is positioned prior to installation.
 3. Install in a solid mopping of Type III or Type IV asphalt, PG 350 Mod Bit Adhesive, or fully torch the burnoff film creating a pool of asphalt. Pay close attention to the sidelap. Do not overheat to expose or compromise the reinforcement.
 4. Position successive rolls using a minimum 6" endlap and 3" side lap. Asphalt bleed out shall be 1/4" to 3/8" on all seams.
 5. Laps may be lightly rolled with a 4" to 6" wide roller to ensure lap is fused.
- Details and flashing may be installed using hot asphalt, cold application or torch techniques. Check project details for proper installation requirements.
- For detailed drawings and recommended installation procedures of typical roof segments, such as drip edge and T-joint conditions, please refer to our website at, www.polyglass.ca.



PRODUCT DATA**

Net Coverage (Approx).....	1.5 m ² (1.50 ft ²)
Weight (Approx)	39 kg (85 lbs)
Thickness (Nominal).....	2.2 mm (90 mils)
Roll Size	1.5 m x 1 m (49'3" x 39 3/8")
Rolls/Pallet.....	25

**All values are nominal at time of manufacturing

APPLICABLE STANDARDS

- ASTM D6163, Type I, Grade S
- UL Classified
- CSA A123.23-15, Type A, Grade 3



PRODUCT CODES

- EF22PPC (Film/Film)
- EF22SS (Sand/Sand)
- EF22PSC (Film/Sand)



www.polyglass.ca

ELASTOFLEX V 22

SBS (ELASTOMERIC) BASE/INTERPLY SHEET

TECHNICAL DESCRIPTION*

Properties		CSA A123.23-15, Type A, Grade 3	Tested Value	
Thickness – mm (mils)		2.0 (80)	2.2 (90)	
Seldge thickness – mm (mils)		2.0 (80)	2.2 (90)	
Mass per unit area – kg/m ² (lbs/100 ft ²)		2.2 (45)	2.7 (108)	
Back surface coating thickness, min. – mm (mils)		1.0 (40)	1.5(60)	
Testing			Before Heat Conditioning	After Heat Conditioning
Strain energy, min. – kN/m (lbf/in)	At 23 ± 2°C (73.4 ± 3.6°F)	See Tested Value	0.5 (2) - MD 0.2 (1) - XMD	0.7 (4) - MD 0.7 (4) - XMD
	At -18 ± 2°C (-4 ± 3.6°F)	See Tested Value	0.5 (3) - MD 0.5 (3) - XMD	0.5 (3) - MD 0.4 (2) - XMD
Peak load, min. – kN/m (lbf/in)	At 23 ± 2°C (73.4 ± 3.6°F)	5.3 (30)	13.7 (78) - MD 7.9 (45) - XMD	13.3 (76) - MD 7.4 (42) - XMD
	At -18 ± 2°C (-4 ± 3.6°F)	12.3 (70)	21.2 (121) - MD 17.9 (102) - XMD	21.7 (124) - MD 14.5 (83) - XMD
Elongation at peak load, %	At 23 ± 2°C (73.4 ± 3.6°F)	2%	5 - MD 4 - XMD	4 - MD 4 - XMD
	At -18 ± 2°C (-4 ± 3.6°F)	1%	5 - MD 5 - XMD	4 - MD 4 - XMD
Ultimate elongation at 23 ± 2°C, %		3%	33 - MD 39 - XMD	11 - MD 13 - XMD
Dimensional stability, max., %		0.5%	0.1 - MD 0.1 - XMD	
Low temperature flexibility, max. – °C (°F)		-18 (-4)	PASS	
Compound stability, min. – °C (°F)		91 (195)	PASS	

*The properties in this table are "as manufactured" unless otherwise noted

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442

www.polyglass.ca

General Line: (888) 410-1375
(954) 233-1330

Customer Service: (800) 222-9782

Technical Service: (866) 794-9659

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 2 years.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit www.polyglass.ca.



www.polyglass.ca