

TECHNICAL INFORMATION SHEET

RubberGard™ MAX (Reinforced) EPDM Membrane



Item Description
1 Roll

Item Number
Various

Product Information

Description:

Firestone RubberGard MAX (Reinforced) EPDM Membrane is an internally reinforced, cured single-ply roofing membrane that features a 9 x 9, 1,000 denier polyester weft inserted reinforcing scrim for increased puncture resistance. It is available in 0.045" (1.1 mm), 0.060" (1.5 mm) and 0.075" (1.9 mm) thicknesses. Designed with fire retardants, Firestone RubberGard MAX EPDM Membrane can meet qualification for UL Class A for slopes up to 3" (76.2 mm), depending on the roofing assembly.

NOTE: Firestone RubberGard MAX FR Membrane is also available if higher slope classification is required.

Product Packaging

Membrane Thickness	Width	Length	Weight
0.045" (1.14 mm)	10' (3.05 m)	100' (30.5 m)	0.32 lb/ft ² (1.6 kg/m ²)
0.060" (1.52 mm)	10' (3.05 m)	100' (30.5 m)	0.42 lb/ft ² (2.1 kg/m ²)
0.075" (1.91 mm)	10' (3.05 m)	100' (30.5 m)	0.55 lb/ft ² (2.7 kg/m ²)

Rolls 10' (3.05 m) wide are no-fold panels.
Please contact your Sales or Customer Service Representative for lead time on 0.075" (1.91 mm) thick membrane.

Method of Application:

1. Substrates must be clean, dry, smooth, and free of sharp edges, fins, loose or foreign materials, oil, grease, and other materials that may damage the membrane.
2. All roughened surfaces that can damage the membrane shall be repaired as specified to offer a smooth substrate.
3. All surface voids greater than ¼" (6.3 mm) wide shall be properly filled with an acceptable fill material.
4. RubberGard MAX EPDM Membrane must be installed in accordance with current RubberGard specifications, details and workmanship requirements.

Storage:

- Store away from sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
- Store away from ignition sources as membrane will burn when exposed to open flame.

Precautions:

- Review Safety Data Sheets (SDS) prior to use.
- Take care when moving, transporting, handling, etc. to avoid sources of punctures and physical damage.
- Isolate waste products, such as petroleum products, greases, oils (mineral and vegetable) and animal fats from the RubberGard membrane.
- It is important that the side of the sheet imprinted with the direction "This Side Down" be installed in direct contact with the substrate to achieve respective test agency compliance.

LEED® Information:

Post-Consumer Recycled Content: 0%
 Post Industrial Recycled Content: 0%
 Manufacturing Location: Prescott, AR

*NOTE: LEED® is a registered trademark of the U.S. Green Building Council.



TECHNICAL INFORMATION SHEET

RubberGard™ MAX (Reinforced) EPDM Membrane

Typical Properties (Meets or exceeds ASTM D4637, Type II scrim-reinforced EPDM Single-Ply roofing membranes)

Physical Test	ASTM Minimum Value	Typical Value 45 mil	Typical Value 60 mil	Typical Value 75 mil
Thickness (D412)	1.143 mm +0.178 mm/-0.127 mm (0.045" +0.007"/-0.005")	1.168 mm (0.046")	---	---
	1.52 mm +0.229 mm/-0.152 mm 0.060" +0.009"/-0.006"	---	1.473 mm (0.058")	---
	1.90 mm +0.279 mm/-0.203 mm 0.075" +0.011"/-0.008"	---	---	1.956 mm (0.077")
EPDM Coating over Scrim (D7635)	0.38 mm (0.015")	0.559 mm (0.022")	0.762 mm (0.030")	0.838 mm (0.033")
Breaking Strength (D751, Grab Method)	400 N (90 lbf)	969.7 N (218 lbf)	880.7 N (198 lbf)	1063.1 N (239 lbf)
Dynamic Puncture Resistance @ 10 J (D5635)	Pass	Pass	Pass	Pass
Static Puncture Resistance @ 25 kg (D5602)	Pass	Pass	Pass	Pass
Elongation, Ultimate % (D412, Die C)	250% Minimum (EPDM only; no scrim)	577%	Pass	Pass
Elongation @ fabric break (ultimate) (D751, Grab Method)	15% MD 15% CD	26.7% MD 35.2% CD	28.0% MD 30.2% CD	27.1% MD 36.3% CD
Tear Strength (D751, B-Tongue Tear)	45 N (10 lbf) Minimum	516.0 N (116 lbf)	516.0 N (116 lbf)	498.2 N (112 lbf)
Brittleness Point (D2137)	-45 °C (-49 °F) Maximum	Pass	Pass	Pass
Ozone Resistance, no cracks (D1149)	Pass	Pass	Pass	Pass
Breaking Strength after Heat Aging*	356 N (80 lbf)	1072.0 N (241 lbf)	Pass	Pass
Elongation, Ultimate after Heat Aging*	200% Minimum (EPDM only; no scrim)	517 %	Pass	Pass
Linear Dimensional Change after Heat Aging*	±1%	-0.8%	Pass	Pass
Water Absorption by Mass	+8%/-2% (EPDM only; no scrim)	+1.0%	Pass	Pass
Factory Seam Strength (D816, Method B)	8.8 kN/m (50 lbf/in) or sheet failure	N/A (no factory seams)	N/A (no factory seams)	N/A (no factory seams)
Visual Inspection after Xenon-Arc Exposure**	Pass	Pass	Pass	Pass
* Heat age EPDM membrane for: 166 ± 1.66 hours at 240 ± 4 °F (116 ± 2 °C), followed by specified physical testing. ** Weather Resistance shall be Practices G151 and G155 Xenon-Arc as follows: <u>Filter Type:</u> Daylight <u>Irradiance:</u> 0.35 to 0.70 W/(m ² ·nm) @ 340 nm [42 to 84 W/(m ² ·nm) @ 300 to 400 nm] <u>Cycle:</u> 690 minutes ± 15 minutes light, 30 minutes light plus water spray <u>Un-insulated Black Panel Temp:</u> 176° ± 4°F (80° ± 2°C) <u>Relative Humidity:</u> 50% ± 5% <u>Spray Water:</u> De-ionized <u>Specimen Rotation:</u> Every 315 KJ/(m ² ·nm) @ 340 nm [37.8 MJ/(m ² ·nm) @ 300 to 400 nm] <u>Exposure:</u> 10,080 KJ/(m ² ·nm) @ 340 nm [1209.6 MJ/(m ² ·nm) @ 300 to 400 nm]				
For use of the product as a component in an air barrier assembly, please consult your Firestone Technical Advisor, Code Agency or Authority having Jurisdiction (AHJ) for the acceptable air barrier assembly details.				

Please contact Firestone Technical Services Department at 1-800-428-4511 for further information.

This sheet is meant to highlight Firestone products and specifications and is subject to change without notice. Firestone takes responsibility for furnishing quality materials which meet published Firestone product specifications. Neither Firestone nor its representatives practice architecture. Firestone offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. Firestone accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Firestone representative is authorized to vary this disclaimer.