

AlphaGuard™ MTS Top Coat

High Performance, One-Part, Moisture Triggered, Polyurethane Top Coat

FEATURES

Moisture Triggered Cure

High Solids Content

Highly Reflective

Single Component

Low Odor

Low VOC

Versatile

BENEFITS

- Uniform cure
- Resists foaming, blisters & pinholes
- Resists wash off
- Yields more dry waterproofing than lower solids products
- Lowers rooftop temperatures resulting in less stress and potential energy savings
- CRRC Listed
- No mixing of multiple components
- No extra labor steps
- No pot life limitations
- Perfect option for odor sensitive accounts/facilities
- Meets all VOC regulation limits
- Suitable for use over many substrates/roof types

DESCRIPTION

AlphaGuard MTS Top Coat is a one-part, moisture triggered, polyurethane liquid applied product.

BASIC USES

The AlphaGuard MTS Top Coat can be used in a variety of applications, including restoration or repair of approved existing roofing substrates, AlphaGuard PLUS system roof assemblies, application to structural concrete roof decks, and in IRMA/PRM and vegetative roof system assemblies. AlphaGuard MTS Top Coat is used as a surfacing over fully-reinforced AlphaGuard MT/MTS Base Coat.

PACKAGING

5 gal (18.9 L) pails

2 gal (7.5 L) pails

COLOR

White

GRADE

Brush, Roller, Spray, Squeegee & Backroll

STORAGE

9 months in unopened containers.

Recommended storage conditions are indoors in a ventilated, dry area removed from heat, open flame, ignition sources, and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Storage life could be affected if the product is not stored properly.

APPLICATION

Surface Preparation: AlphaGuard MT/MTS Base Coat or Top Coat surface must be cured, clean, dry, in sound condition, and free of dirt, debris, and contaminants prior to application.

Mixing: Mechanical mixing is typically not necessary. Ensure product is consistent in appearance and viscosity. Do not thin.

Priming: AlphaGuard MT/MTS Base and Top Coats should be top-coated within 72 hours of application. If cured base or top coat is exposed for longer than 72 hours, an application of Geogard Primer will be required to promote adhesion between coats. Review the recommended primer product data sheet for specific product and application information.

Installation: Install product using one of the approved application methods evenly at the recommended coverage rate. Use wet mil gauges to monitor coverage rates throughout application.

AlphaGuard™ MTS Top Coat

APPLICATION CONTINUED

ACCEPTABLE ROOF SURFACES

COVERAGE RATES

TEMPERATURE/WEATHER RECOMMENDATIONS

CURE TIMES

SPRAY EQUIPMENT RECOMMENDATIONS

CLEAN UP

LIMITATIONS

Non-Skid Application: Install an additional layer of top coat in white or chosen color at 1-1½ gal / 100 sq. ft. (16-24 wet mils) (0.4-0.6 L/m²) and immediately broadcast and backroll an approved non-skid media. Color striping can be installed in 3-4" wide areas along the perimeter of the walkway area at a coverage rate of 1-1½ gal / 100 sq. ft. (16-24 wet mils) (0.4-0.6 L/m²) to provide identification of the areas on the roof.

Approved Non-Skid Media:

- Silica Sand (20-40 mesh) - Coverage: 20-30 lbs. / 100 sq. ft.
- No. 11 Roofing Granule - Coverage: 10-15 lbs. / 100 sq. ft.

BUR Gravel	BUR Smooth	Concrete	MB Granule	MB Smooth	Metal/ Metal Fluoropolymer	Single Ply	SPUF	Walls
	●	●	●	●		●		

Top Coat: 2 gals / 100 sq. ft. (0.8 L/m²) (32 wet mils)

Tremco Plain and Simple/Extended Warranty: 3 gals / 100 sq. ft. (1.2 L/m²) (48 wet mils)

Non-Skid Coat: 1-1½ gals / 100 sq. ft. (0.4 - 0.6 L/m²) (16-24 wet mils)

Note: Coverage rates are listed at minimum recommended rates. The application surface can affect the necessary coverage rate. Color top coats may require higher coverage rates or additional coats to provide adequate hiding and consistent appearance.

Min Ambient: 50°F (10°C)

Max Ambient: 110°F (43.3°C)

- Minimum temperatures must be rising following application
- Do not apply when dew point is within 5°F (2.7°C) of ambient temperatures
- Do not apply when precipitation, fog or dew is imminent prior to cure of the product

Skin Time:

1 hour @ 85°F (29°C) / 70% RH

2-3 hours @ 68°F (20°C) / 70% RH

4-6 hours @ 50°F (10°C) / 70% RH

Over-Coat Time:

2-4 hours @ 85°F (29°C) / 70% RH

6-10 hours @ 68°F (20°C) / 70% RH

16-18 hours @ 50°F (10°C) / 70% RH

Note: Cure times can be effected by a number of weather and jobsite conditions including but not limited to exposure to sunlight and wind, humidity, precipitation, and temperature.

GENERAL GUIDELINES

Component: Single-Component

Pressure: 4,000 - 5,500 psi minimum

Tip Size: .039 - .049

Filters: Remove

Hose Type: High Pressure

WHIP: 1/4" High Pressure

Product Temp: 100 - 110°F (37 - 43°C)

- Must use heavy duty or industrial grade spray tips
- Properly clean and maintain spray equipment before, during, and after use
- Equipment should be properly grounded during use

Before the product cures, clean surfaces and equipment with isopropyl alcohol, mineral spirits, or xylene..

Spray equipment can be flushed/cleaned using MEK or xylene.

Not recommended for use over the following:

Roof Decks: Cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).

LIMITATIONS CONTINUED

PHYSICAL PROPERTIES

CODES & APPROVALS

MAINTENANCE

PRECAUTIONS

TECHNICAL SUPPORT



Roofing & Building Maintenance

www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building
Maintenance is a part of the Tremco
Construction Products Group

AlphaGuard™ MTS Top Coat

Products/Systems: Asphalt-based or coal tar gravel surfaced BUR systems, clay tile, corrugated or standing seam metal roof systems, expanded or extruded polystyrene insulation, fluoropolymer finished metal, shingles, silicone-based products, and tar-based products.

- Not for use under continuous immersion.

PROPERTY	TEST METHOD	TYPICAL VALUE
Abrasion Resistance	ASTM D4060	37 mg
Accelerated Weathering (4,500 hrs)	ASTM G154	Pass
Breaking Strength	ASTM D751	244 lbf/in
Crack Spanning	ASTM C1305	Pass - 2 mm / 0.08 in
Dimensional Stability	ASTM D1204	0%
Dynamic Puncture Resistance	ASTM D5635	50 J
Elongation	ASTM D412	250%
Flexibility	ASTM D522	Pass @ -40°F
Indentation Hardness	ASTM D2240	77 Shore A
Low Temperature Flexibility	ASTM D5147	Pass @ -50°F
Peak Load	ASTM D5147	447 lbf/in
Permeance	ASTM E96	0.021 perm-in
Static Puncture Resistance	ASTM D5602	95 lbf
Tear Strength	ASTM D751	215 lbf
Tensile Strength	ASTM D412	1,843 psi
Water Absorption	ASTM D95	0.1%
Water Vapor Transmission	ASTM E96	16 g/m ² per day
Volume Solids	ASTM D2697	87-89%
Weight Solids	ASTM D1644	88-90%
VOC		< 50 g/L

AlphaGuard MTS System Testing

Florida Building Code



	Initial	Rapid Ratings*	Weathered
Solar Reflectance	<u>0.83</u>	<u>0.82</u>	Pending
Thermal Emittance	<u>0.9</u>	<u>0.9</u>	Pending
Rated Product ID	<u>0612-0025</u>		
Licensed Manufacturer ID	<u>0612</u>		
Classification	<u>Production Line</u>		

RAPID RATINGS

*CRRC Rapid Ratings: These are interim laboratory-aged values that simulate weathered values. These values will be replaced by the measured three-year aged values upon completion of the weathering process.

Cool Roof Rating Council ratings are determined for a fixed set of conditions, and may not be appropriate for determining seasonal energy performance. The actual effects of solar reflectance and thermal emittance on building performance may vary.

Manufacturer of product stipulates that these ratings were determined in accordance with the applicable Cool Roof Rating Council procedures.

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.