



**USES:  
BASE PLY  
FLASHING REINFORCING SHEET**

## PARADIENE® 20 TS SA F

### Commercial Product Data Sheet

Paradiene 20 TS SA F is the modified bitumen base ply of the semi-adhered Paradiene 20 TS SA/Paradiene 30 TG System. Designed for use in homogeneous multi-layer modified bitumen roof membrane systems, Paradiene 20 TS SA F consists of a lightweight random fibrous glass mat impregnated and coated with elastomeric styrene-butadiene-styrene (SBS) modified bitumen. The unique back surface design consists of factory-applied, self-adhesive stripes applied over a proprietary acrylic coating and is lined with split, high-strength polyolefin release film, which provides for uniform bonding of approximately 50% of the total surface area of the sheet.

Contact Siplast for information on approved product uses.

### PRODUCT INFORMATION

#### Application

Refer to the Siplast Technical Guide for detailed application information and slope limitations. Paradiene 20 TS SA F is lapped 3 inches (76 mm) side and end.



#### Storage and Handling

All Siplast roll roofing products should be stored on end on a clean, flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

#### Packaging

Pallet: 41 in x 48 in (104 cm x 122 cm) wooden pallet  
 Rolls Per Pallet: 25  
 Pallets Per Truckload: 20  
 Minimum Roll Weight: 76 lb (34.5 kg)


#### Listings, Approvals, & Certifications



Standards	ASTM D6163 Type I, Grade S; CSA A123.23-15 Type A, Grade 1
Roll Length	Min: 33.5 ft (10.21 m)
Roll Width	Avg: 3.28 ft (1.00 m)
Coverage	1.0 Square (9.3 m <sup>2</sup> )
Coverage Weight Per Square	Min: 76 lb (3.7 kg/m <sup>2</sup> )
Laying Lines	3 in (76 mm) Line Color: White
Top Surfacing	Perforated Polypropylene Film
Back Surfacing	Adhesive Stripes Applied Over Acrylic Coating
Product Options	RoofTag

Current copies of all Siplast Commercial Product Data Sheets & Safety Data Sheets are posted on our website at [www.siplast.com](http://www.siplast.com)  
 Rev Date 5/2022

**U.S. TEST STANDARDS**

Property (as Manufactured)	Values / Units	Test Method
*Thickness (minimum)	94 mils (2.4 mm)	ASTM D5147 Section 6
*Thickness (average)	98 mils (2.5 mm)	ASTM D5147 Section 6
**Peak Load @ 73.4°F (23°C) (average)	30 lbf/inch (5.3 kN/m)	ASTM D5147 Section 7
**Peak Load @ 0°F (-18°C) (average)	70 lbf/inch (12.3 kN/m)	ASTM D5147 Section 7
**Elongation @ Peak Load 73.4°F (23°C) (average)	3%	ASTM D5147 Section 7
**Elongation @ Peak Load 0°F (-18°C) (average)	3%	ASTM D5147 Section 7
**Ultimate Elongation @ 73.4°F (23°C) (average)	70%	ASTM D5147 Section 7
**Tear Strength (average)	40 lbf (0.18 kN)	ASTM D5147 Section 8
Water Absorption (maximum)	1%	ASTM D5147 Section 10
Dimensional Stability (maximum)	0.1%	ASTM D5147 Section 11
Low Temperature Flexibility (maximum)	-15°F (-26°C)	ASTM D5147 Section 12
***Compound Stability (minimum)	250°F (121°C)	ASTM D5147 Section 16
Coating Thickness – Back Surface	≥40 mils (1 mm)	ASTM D5147 Section 17
Cyclic Fatigue	Paradiene 30 FR bonded to Paradiene 20, with an approved method of attachment, passes ASTM D5849 both as manufactured and after heat conditioning, according to ASTM D5147.	
*Thickness does not include the thickness of the adhesive stripes. **The value reported is the lower of either MD or XD. ***The high temperature stability of the self-adhesive bitumen coating is 212°F (100°C)		The above properties have been validated by PRI and are under continuous follow-up to ensure compliance. The product has been validated to meet ASTM D6163-08, Type II, Grade S.

**CANADA TEST STANDARDS**

Property (as Manufactured)	Values / Units	Test Method
*Thickness (minimum)	2.4 mm (94 mils)	CSA A123.23-15
*Thickness (average)	2.5 mm (98 mils)	CSA A123.23-15
**Peak Load @ 23°C (73.4°F) (average)	5.3 kN/m (30 lbf/inch)	CSA A123.23-15
**Peak Load @ -18°C (0°F) (average)	12.3 kN/m (70 lbf/inch)	CSA A123.23-15
**Elongation @ Peak Load 23°C (73.4°F) (average)	3%	CSA A123.23-15
**Elongation @ Peak Load -18°C (0°F) (average)	3%	CSA A123.23-15
**Ultimate Elongation @ 23°C (73.4°F) (average)	70%	CSA A123.23-15
Dimensional Stability	0.1%	CSA A123.23-15
Low Temperature Flexibility (maximum)	-26°C (-15°F)	CSA A123.23-15
***Compound Stability (minimum)	121°C (250°F)	CSA A123.23-15
Coating Thickness – Back Surface	≥1 mm (40 mils)	CSA A123.23-15
*Thickness does not include the thickness of the adhesive stripes. **The value reported is the lower of either MD or XD. ***The high temperature stability of the self-adhesive bitumen coating is 212°F (100°C)		