

SOPRAPLY STICK TRAFFIC CAP

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 240212SCANE

supersedes 230919SCANE)

DESCRIPTION

SOPRAPLY STICK TRAFFIC CAP is a high performance cap sheet membrane composed of SBS modified bitumen and a composite reinforcement. The surface is protected by coloured granules and the self-adhesive underface is covered with a split-back silicone release film.

SOPRAPLY STICK TRAFFIC CAP is provided with DUO SELVEDGE technology which allows the immediate sealing of the membrane along side laps.

SURFACE PREPARATION

Surfaces must be clean, dry and free of loose particles. The membrane is installed over the substrate previously primed with one of the ELASTOCOL STICK primers.

INSTALLATION

SELF-ADHESIVE

SOPRAPLY STICK TRAFFIC CAP is adhered to the substrate by peeling off the silicone release film.

Once the membrane is in place, apply pressure over the whole surface using a membrane roller to ensure a complete and uniform adhesion.

Apply cold adhesive on the first 100 to 125 mm (4 to 5 in) of the end laps and weld the last 25 to 50 mm (1 to 2 in) using a hot air welder.

Finish the application by welding the last 25 mm (1 in) of the side lap using an electric hot-air welder and a membrane roller. The use of an automatic hot-air welder will greatly increase the speed and quality of the seal.

Minimum application temperature: 0 °C (32 °F)

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

GENERAL INFORMATION

Specifications	SOPRAPLY STICK TRAFFIC CAP	
Reinforcement	Composite	
Dimensions	10 x 1 m (33 x 3,3 ft)	
Selvedge width	100 mm (4 in)	
Surface	Granules	
Underface	Self-adhesive, covered with a split-back silicone release film.	

(All values are nominal)









SOPRAPLY STICK TRAFFIC CAP

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 240212SCANE

supersedes 230919SCANE)

PROPERTIES

Properties	SOPRAPLY STICK TRAFFIC CAP		CSA A123.23
	BEFORE Heat Conditioning	AFTER Heat Conditioning	Type C, Grade 1 Requirements
Thickness, min.	3.8 mm (150 mils)		2.8 mm (110 mils)
Selvedge thickness, min.	2.8 mm (110 mils)		1.8 mm (70 mils)
Mass per unit area, min.	4.8 kg/m² (100 lb/100 ft²)		2.9 kg/m² (60 lb/100 ft²)
Strain energy, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	8/6.5 kN/m (46/37 lbf/in) 8/7 kN/m (46/40 lbf/in)	7/6 kN/m (40/34 lbf/in) 6.5/6 kN/m (37/34 lbf/in)	5.5 kN/m (31 lbf/in) 3.0 kN/m (17 lbf/in)
Peak load, min. MD/XD, at 23 °C \pm 2 °C (73.4 °F \pm 3.6 °F) at -18 °C \pm 2 °C (0 °F \pm 3.6 °F)	17/14 kN/m (97/80 lbf/in) 22/19 kN/m (126/108 lbf/in)	18/15 kN/m (103/86 lbf/in) 22/17 kN/m (126/97 lbf/in)	Report value Report value
Elongation at peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	55/55% 45/45%	50/50% 35/35%	Report value Report value
Ultimate elongation, MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F)	65/65%	55/55%	Report value
Dimensional stability, max. MD/XD	±0.2/±0.2%		0.5%
Low temperature flexibility, max. MD/XD	-27/-27 °C (-17/-17 °F)	-18/-18 °C (-0.4/-0.4 °F)	-18 °C (-0.4 °F)
Low temperature flexibility after UV weathering, max. MD/XD	-12/-12 °C (10/10 °F)		-12 °C (10 °F)
Compound stability	91/91 °C (196/196 °F)		min. 91 °C (195 °F)
Resistance to puncture	Pass		Pass
Granule embedment	< 2.0 g (0.07 oz)		max. 2.0 g (0.07 oz)

(All values are nominal)

STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.





