



**USES:
FINISH PLY
FLASHING SHEET**

PARADIENE® 40 FR BW

Commercial Product Data Sheet

Paradiene 40 FR BW is a modified bitumen finish ply and flashing sheet. Designed for use in homogeneous multi-layer modified bitumen roof membrane systems, Paradiene 40 FR BW consists of a fiberglass scrim/fiberglass mat composite impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen and is surfaced with highly reflective, white mineral granules.

Contact Siplast for information on approved product uses.

PRODUCT INFORMATION

Standards	ASTM D6163 Type II, Grade G; CSA A123.23-15 Type B, Grade 1
Roll Length	Min: 26.0 ft (7.92 m)
Roll Width	Avg: 3.28 ft (1.00 m)
Coverage	0.75 Square (7.0 m ²)
Coverage Weight Per Square	Min: 98 lb (4.78 kg/m ²)
Selvage Width	Avg. 3.75 in (95 mm) Orange laying line is 4 in (102 mm) from the edge of the sheet.
Selvage Surfacing	Silica Parting Agent
Top Surfacing	Bright White Mineral Granules
Back Surfacing	Silica Parting Agent
Product Options	RoofTag

Application

Refer to the Siplast Technical Guide for detailed application information and slope limitations. Paradiene 40 FR BW is lapped 4 inches (102 mm) at sides and 6 inches (152 mm) at ends.



Storage and Handling

All Siplast roll roofing products should be stored on end on a clean, flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging


Pallet: 41 in x 48 in (104 cm x 122 cm) wooden pallet
Rolls Per Pallet: 25
Pallets Per Truckload: 20
Minimum Roll Weight: 74 lb (33.5 kg)

Listings, Approvals, & Certifications



Current copies of all Siplast Commercial Product Data Sheets & Safety Data Sheets are posted on our website at www.siplast.com
Rev Date 8/2022

U.S. TEST STANDARDS

Property (as Manufactured)	Values / Units		Test Method
Thickness (average)	157 mils (4 mm)		ASTM D5147 Section 6
*Thickness at Selvage	130 mils (3.3 mm) avg.	126 mils (3.2 mm) min.	ASTM D5147 Section 6
**Peak Load @ 73.4°F (23°C) (average)	80 lbf/inch (14.31 kN/m)		ASTM D5147 Section 7
**Peak Load @ 0°F (-18°C) (average)	150 lbf/inch (26.5 kN/m)		ASTM D5147 Section 7
**Elongation @ Peak Load 73.4°F (23°C) (average)	5%		ASTM D5147 Section 7
**Elongation @ Peak Load 0°F (-18°C) (average)	4%		ASTM D5147 Section 7
**Ultimate Elongation @ 73.4°F (23°C) (average)	80%		ASTM D5147 Section 7
**Tear Strength (average)	120 lbf (0.54 kN)		ASTM D5147 Section 8
Water Absorption (maximum)	1%		ASTM D5147 Section 10
Dimensional Stability (maximum)	0.1%		ASTM D5147 Section 11
Low Temperature Flexibility (maximum)	-15°F (-26°C)		ASTM D5147 Section 12
Granule Embedment	1.5 grams per sample Max. avg. loss	2.0 grams per sample Max. individual loss	ASTM D5147 Section 15
Compound Stability (minimum)	250°F (121°C)		ASTM D5147 Section 16
Cyclic Fatigue	Paradiene 40 FR BW bonded to Paradiene 20, with an approved method of attachment, passes ASTM D5849 both as manufactured and after heat conditioning according to ASTM D5147.		
*Measured on the selvage edge excluding the granule surfacing. **The value reported is the lower of either MD or XD.			The above properties have been validated by PRI and are under continuous follow-up to ensure compliance. The product has been validated to meet ASTM D6163-08, Type II, Grade G.

CANADA TEST STANDARDS

Property (as Manufactured)	Values / Units		Test Method
Thickness (average)	4 mm (157 mils)		CSA A123.23-15
*Thickness at Selvage	3.3 mm (130 mils) avg.	3.2 mm (126 mils) min.	CSA A123.23-15
**Peak Load @ 23°C (73.4°F) (average)	14.1 kN/m (80 lbf/inch)		CSA A123.23-15
**Peak Load @ -18°C (0°F) (average)	26.5 kN/m (150 lbf/inch)		CSA A123.23-15
**Elongation @ Peak Load 23°C (73.4°F) (average)	5%		CSA A123.23-15
**Elongation @ Peak Load -18°C (0°F) (average)	4%		CSA A123.23-15
**Ultimate Elongation @ 23°C (73.4°F) (average)	80%		CSA A123.23-15
Dimensional Stability (maximum)	0.1%		CSA A123.23-15
Low Temperature Flexibility (maximum)	-26°C (-15°F)		CSA A123.23-15
Granule Embedment	1.5 grams per sample Max. avg. loss	2.0 grams per sample Max. individual loss	CSA A123.23-15
Compound Stability (minimum)	121°C (250°F)		CSA A123.23-15
*Measured on the selvage edge excluding the granule surfacing. **The value reported is the lower of either MD or XD.			

SOLAR REFLECTANCE / THERMAL EMITTANCE

Property (as Manufactured)	Values / MD	Values / XMD	Test Method
Solar Reflectance (avg.)	0.74		ASTM C1549
Thermal Emittance (avg.)	0.91		ASTM C1371
Solar Reflectance Index (avg.)	92		ASTM E1980